

Company	Nature Babies Limited Unit 17 Clearview Farm 103 Loughborough Road Quorn Leicester LE12 8DU
Contact	Isobel Parr

TEST REPORT: TN 384943

Identification	One sample of nappy
Order No	Not Stated
Date Received : 27 February 08	Date Issued : 04 March 08

Sample No	Description	Stated Composition	Care Label	End Use	Quality
1	Bamboo Lovable	Not Stated	60°C (1 Bar) Low Tumble	Disposable Nappy	Not Stated

Method	Test	Performance Code ²	Pass/Fail ²
Long-Tail	Colour Fastness to Rubbing - sample 1	Long-Tail	Pass
Long-Tail	Product Cleanse - sample 1	Reusable Nappies	Fail
European Parliament Directive	Fibre Composition - sample 1	N/A	N/A

RESULTS**Long-Tail Method Of Test****Product Cleanse to Mothercare 2A @ 60°C Low Tumble Dry**

Assessment carried out to Long Tail Performance Standards

Sample 1- Nappy

Assessment

Cross Staining	4-5
Shade Change	2-3
Spirality	None apparent
Fraying Of Fabric/Trims	Has occurred to edges of nappy
Detachment Of Fastenings/Trims	Not Detached
Pilling / Fuzzing of Surface Fibres	4
Differential Shrinkage of Components/Parts	No Changes Observed.
Unravelling / Breaks In Stitching	No unravelling / breaks observed
Other Changes	None observed

Sample 1- Nappy Inner

Assessment

Cross Staining	4-5
Shade Change	2-3
Spirality	None apparent
Fraying Of Fabric/Trims	Has occurred to nappy inner
Detachment Of Fastenings/Trims	Not Detached
Pilling / Fuzzing of Surface Fibres	4
Differential Shrinkage Of Components/Parts	No Changes Observed.
Unravelling / Breaks In Stitching	No unravelling / breaks observed
Other Changes	None observed

Colour Fastness to Rubbing : BS EN ISO 105 – X12 : 1995

Tested in accordance with Long-Tail test methods.

	<u>Staining on cotton lawn</u>			
	<u>Dry</u>	<u>Wet</u>		<u>Wet</u>
	<u>Warp</u>	<u>Weft</u>	<u>Warp</u>	<u>Weft</u>
Main	4-5	4-5	4-5	4-5
Lining	4-5	4-5	4-5	4-5

European Parliament Directive Method Of Test

Qualitative & Quantitative Analysis of Fibre Mixture : 73/44/EEC and 96/73/EC
(as amended) Method 7

The analysis was conducted in accordance with the methods for quantitative analysis described in Directive 96/73/EC (as amended). The results relate to the overall composition of the sample submitted unless stated, and are based on clean, dry mass, with allowances for moisture and other matter, as given in Annex 11 of the EEC Directive on Textile Descriptions 96/74/EC (as amended).

Allowance:
 Viscose 13.00%
 Polyester 1.50%

Sample 1

	<u>% Composition</u>	
	<u>Viscose</u>	<u>Polyester</u>
Outer	88.7	11.3
Lining	88.6	11.4
Stuffable Pad	87.3	12.7

Please note that as no expected composition was supplied we are unable to apply a test of reasonableness to the results of the 73/44/EEC and 97/73/EC test. Attention to this is required prior to labelling your products.

Audrey White
Audrey White
Manager - Textiles